



The Open Biotechnology Journal

Content list available at: <https://openbiotechnologyjournal.com>



REVIEW ARTICLE

Bacterial Cellulose from Food to Biomedical Products

Supajit Sraphet¹ and Bagher Javadi^{2,*}

¹Institute of Molecular Biosciences, Mahidol University, Nakhon Pathom, Thailand

²Department of Sciences, Faculty of Science and Technology, Suan Sunandha Rajabhat University, Bangkok, Thailand

Abstract:

Cellulose production of aerobic bacteria with its very unique physiochemical properties attracted many researchers. The biosynthetic of Bacterial Cellulose (BC) was produced by low-cost media recently. BC has been used as biomaterials and food ingredient these days. Moreover, the capacity of BC composite gives the numerous application opportunities in other fields. Bacterial Cellulose (BC) development is differentiated from suspension planktonic culture by their Extracellular Polymeric Substances (EPS), down-regulation of growth rate and up-down the expression of genes. The attachment of microorganisms is highly dependent on their cell membrane structures and growth medium. This is a very complicated phenomenon that optimal conditions defined the specific architecture. This architecture is made of microbial cells and EPS. Cell growth and cell communication mechanisms effect biofilm development and detachment. Understandings of development and architecture mechanisms and control strategies have a great impact on the management of BC formation with beneficial microorganisms. This mini-review paper presents the overview of outstanding findings from isolating and characterizing the diversity of bacteria to BC's future application, from food to biosensor products. The review would help future researchers in the sustainable production of BC, applications advantages and opportunities in food industry, biomaterial and biomedicine.

Keywords: Bacterial cellulose, Molecular characterization, Biomedicine, Food products, Cellulose production, Forms of bacterial cellulose.

Article History

Received: June 27, 2020

Revised: September 16, 2020

Accepted: October 7, 2020

1. INTRODUCTION

Microorganisms are usually defined with their planktonic and suspension cell growth characterizations. Attachment of microorganisms on the surface exhibited the specific phenotypes. These phenotypic distinctions are due to gene expressions and growth rate. Therefore, biofilms showed the unique surface attachment-detachment, community structure and finally micro-ecosystems. Bacterial cellulose (BC) is a natural nanomaterial of exopolysaccharide biofilm from many bacterial genera such as *Acetobacter*, *Sarcina* and *Agrobacterium* and *Komagataeibacter* (former *Gluconacetobacter*) [1]. *Komagataeibacter* can produce BC while cultivated in a medium supplied with carbon and nitrogen [2]. The priority of BC production by this genus is due to their higher yield and purity. However, the species and strains biofilm structure and mechanical properties are different [3].

Chinese reported BC firstly during their ancient production of fermented beverage kombucha tea. They observed the co-colony of acidic acid bacteria and yeast embedded on the

beverage surface [4]. Generally, the microbial biofilm and in particular, BC production are the self-defense strategy towards sustainable acquiring and securing nutrients supply in harsh environments [5]. Many multi-step regulated mechanisms with the help of enzymes and catalytic complexes rigorously control the cell's BC synthesis reactions. Although, 1,4- β -glucan chains formation and their assembly to cellulose inside and outside of the bacterial cell are the main two steps of BC synthesis [5 - 7] (Fig. 1).

The main advantage of BC is the purity of cellulose. Impurities of lignin, hemicelluloses, and pectin in plant derived cellulose enforced the application of harsh chemicals in purification process (environmental safety); however BC purification process needs low energy [8, 9]. Unique properties of BC include crystallinity indexes up to 85% [10], a higher degree of polymerization, significant tensile characterization [11 - 13], a specific area in BC fibers, higher water holding capacity, and longer drying time [14 - 16]. These unique features are related to the high aspect ratio of fibrils, which made the increased surface area hold higher water capacity and tightly bound them to hydroxyl groups. BC generally is very flexible and easy to modify based on its many reactive groups. High porosity and surface area make BC appropriate for physical and chemical interactions with many compounds,

* Address correspondence to this author at the Department of Sciences, Faculty of Science and Technology, Suan Sunandha Rajabhat University, Bangkok, Thailand; Tel: +66-02-160-1143-45; Fax: +66-02-160-1146; E-mail: Javadi.ba@ssru.ac.th

including antimicrobials [10, 17, 18] (Fig. 2).

Many factors control and structure the BC yield and properties. Bacterial strains, medium composition and cultivation process mainly determine the morphology, properties and eventually range of possible application of BC. Several BC applications were recently developed, for example, biomedical applications of BC mostly focused on materials for tissue engineering, wound dressing, artificial skin, blood vessels, and carriers for drug delivery [1, 12] (Fig. 3).

Optimization of the production line from strain selection to final modification needs much effort in research. Achieving these goals attracted many researchers to explore better BC producing species/ strains and low-cost media. It is noteworthy

to mention that replacing the expensive media Hestrin and Schramm (HS) has been done by many researchers [19 - 23]. However, the BC produced purity was in less degree as those required for some applications such as biomedical and industrial applications.

The production of cellulosic bacteria generally includes the two main steps, bacterial strain and bioprocess production. Static and stirred cultivation, besides semi-continuous or continuous fermentation methods, are the major bioprocess productions. The shapes and properties of final cellulose products are in significant dependence to the strain of bacteria, static, agitated, batch or feed batch production processes [24]. This review paper presents an overview of outstanding findings in BC production and applications.



Fig. (1). Bacterial cells and 1,4-β-glucan chains (microfibrils) exopolysaccharides.




Fig. (2). The main advantage of the Bacterial Cellulose (BC).




Fig. (3). Factors control and structure the BC yield and properties, applications of BC.

2. STRAIN SELECTION

Naturally, the bacterial species of *Achromobacter* [25, 26], *Alcaligenes* [27], *Aerobacter* [28, 29], *Agrobacterium* [30 - 33], *Azotobacter* [6], *Gluconacetobacter* [19, 34, 35], *Pseudomonas* [36], *Rhizobium* [37, 38], *Sarcina* [39] and *Dickeya* and *Rhodobacter* [40] can produce cellulose.

However, the *Gluconacetobacter* genus is the primary group of BC producers. This fact is due to the wide range of

carbon and nitrogen sources used by the *Gluconacetobacter* genus [7, 41]. In recent days with biotechnology, the engineered bacteria with low consuming nutrients and high yield were produced [41, 42]. For example, *Komagataeibacter rhaeticus* was engineered and fully sequenced with low nitrogen and high yield. It is noteworthy to mention that genetic tool kit was developed for this bacterium to engineer the desired bacteria recently [43].




Fig. (4). Genetic mechanisms of cellulose production. Cellulose synthase (4p02.pdb).

3. GENETIC MECHANISMS OF CELLULOSE PRODUCTION

Uridine diphosphoglucose (UDPGlc) synthesis and polymerization of glucose are the two main cellulose production steps in bacteria. The polymerization is achieved by cellulose synthase, which formed an unbranched chain of 1,4-β-glucan. Naturally, carbon compound of hexoses, glycerol, dihydroxyacetone, pyruvate, and dicarboxylic acids entering the Krebs cycle, gluconeogenesis or the pentose phosphate cycle, followed by phosphorylation and isomerization and finally UDPGlc pyrophosphorylase converts the compounds into UDPGlc, a precursor for the cellulose production. The efficiency of this production is different in different bacteria, for example, for *A. xylinum* is 50% [27] (Fig. 4). Remarkable genetic engineering approach was presented recently. In this approach, the most efficient microbial BC producer, *Komagataeibacter rhaeticus* iGEM, was isolated, and its full genome was sequenced. This bacterium was then engineered for functionalization of cellulose production. The functionalization engineering results will help other researchers apply a similar method for producing the more specific BC with unique pattern for biomaterial applications [43].

4. CULTURE MEDIUM

BC medium is costly, as it needs a high demand of glucose and other nutrients [44]. Hestrin and Schramm (HS) medium (glucose, peptone, and yeast extract) is used for BC production; however, the uses of the wastes, foods, and fruits as a medium have been reported recently [44 - 50]. For example, fruit juices such as orange, pineapple, apple, Japanese pear, and grape

showed a higher yield in *Acetobacter xylinum* BC production [46]. Furthermore, other fruits such as pineapple, pomegranate, muskmelon, watermelon, tomato, orange, and also molasses, starch hydrolysate, sugarcane juice, coconut water, coconut milk were used as carbon sources [44]. The same properties of BC from these sources were reported with more expensive media [48]. Organic acid, carbohydrates, ethanol, and acetic acid, have been used as additives in BC production media [51, 52] (Fig. 5).

Optimization of the media during the process is the key to succeed in producing sustainable BC. Many factors such as pH, oxygen supply, and temperature should be controlled and optimized during the process [7, 41]. All of these factors affect the yield and properties of the final products. The pH and temperature are highly dependent to the species and strain of bacteria. Generally, pH could be between 4.0- 7.0. On the other hand, the pH of the culture can directly control the accumulation time and the secondary metabolite. This can affect nutrition supply in the process. For example, the dried weight of BC in *Acetobacter xylinum* 0416 was 60% higher in the control pH system compared to the uncontrolled. Furthermore, this bacterium's growth rate was 30% higher in lower pH conditions [53]. Also, aeration and oxygen optimization can play a critical role in BC production. Insufficient oxygen supply inhibits bacterial growth, and high oxygen supply favor gluconic acid production [7, 51, 54]. Temperature as an essential factor in BC production should optimize carefully. For example, optimal *Komagataeibacter xylinus* B-12068 temperature growth is preferably 28-30 °C [52] (Fig. 6).




Fig. (5). Cellulose production by different strains of *A. xylinum*.




Fig. (6). Cellulose production of different species.

5. CULTIVATION METHODS

The cultivation mode of the BC can be static or agitated. Static modes of cultivation usually take 5-20 days due to the bacterial strain and nutrients supply. The production is generally on the area of air/ liquid interface [24]. The final BC membrane shape depends on the material used for growing the BC in this method. This method used for the predefined shape of BC required. Disadvantages of this mode of action include low yield and more time consumption. [55, 56]. Fed-batch cultivation could help to overcome these problems [56]. Researchers showed two to three times' higher yields with fed-batch culture compared to batch cultivation [49]. Specific bioreactors were produced to use in the static mode culture of BC recently [57, 58]. Another mode of cultivation is agitated, which has a more oxygen supply therefore, the yield is higher than the static mode [59]. The shape of BC final product depends on the agitation speed. The drawback of the agitate mode of cultivation is the production of cellulose-negative mutants population. This mutant can produce BC with different properties as a subpopulation. To overcome this problem, the use of ethanol as a supplement nutrient is recommended [50, 58, 60, 61]. Stirred tank bioreactor can be used in the agitated mode for BC production. Shear stress is a great drawback of this BC production mode [62, 63]. Airlift bioreactor is another bioreactor with better efficient results [54]. In this bioreactor the oxygen supply is provided from the bottom of the tank, therefore preparing better BC production conditions [64].

6. SCRUTINIZING THE BC FORMATION: FROM PLANKTONIC CELL TO BIOFILM

Many researchers observed the biofilm in general with a simple microscope [65, 66]. However, the high-resolution electron microscope allowed us to examine the specific

detailed characterizations of microbial biofilms [67]. It is noteworthy to mention that Ruthenium red (that stains the polysaccharide) facilitated the 'researcher's effort to show the matrix (structure) of biofilm based on the polysaccharide. Furthermore, the gene regulation studies and utilization of laser scanning microscope had a significant impact on understanding biofilm formation and characterization [67 - 69]. Traditionally biofilm is defined as the assemblage of 'microorganism's cells on the surface. This structure is irreversibly associated with themselves and the surrounding matrix. Biofilm matrix has a unique structure base on the cell and non-cellular materials of the medium. The main feature of biofilm is attachments that can be defined as unique substratum interactions, culture medium, hydrodynamic of aqueous environment and cell surface characteristics. These features are very important for scrutinizing the BC formation specifically and bacterial biofilm formation in general. Substratum is considered as the solid surfaces such as tissue, indwelling medical devices, industrial devices (piping), and natural aquatic systems. The physicochemical features of the surface play an important role in attachment; these features can effect on rate and extent of biofilm formation. Rough hydrophobic nonpolar surfaces are more favorable for rapid biofilm formation [70 - 74]. It is important to note that the surface of materials in an aqueous environment could facilitate and increase biofilm formation speed [75, 76]. The hydrodynamic of the environment with flow velocity could control biofilm formation (the higher velocity made thinner biofilm boundary layer). Furthermore, the settle down of cell suspension in the aqueous medium can control flow velocity [77 - 79].

The medium characteristics have a great impact on biofilm formation. pH, nutrient level, and temperature can play a substantial role in forming biofilm [80 - 84]. It is important to

recall here that bacterial cell surface properties such as hydrophobicity and flagella influence the attachment and rate of biofilm formation. Furthermore, the production of EPS has a great impact on biofilm development [85 - 88]. Genes regulations have a countless effect on biofilm formation; for example, in *Pseudomonas aeruginosa algC* gene up regulation was observed during the bacterial attachments [89].

Moreover, polyphosphokinase synthesis genes in *Pseudomonas aeruginosa* were up-regulated [90]. The up-regulated genes in *Staphylococcus aureus* genes involved in the glycolysis pathway was reported previously [91]. The detailed information on gene regulation of biofilm formation was reviewed earlier [91].

7. DOWNSTREAM PROCESSING

These parts of the production consist of separation of BC from media and purification of biopolymers. The BC can remove easily from static mode cultivation by separation. In agitated mode BC removes from the media by centrifugation or filtration. The alkali treatment will do the purification of cellulose with NaOH or KOH [5, 6]. The level of purification is depending to the final application, for example we need more purify cellulose for biomedical applications compare to the food application. Sometimes drying step adds to the downstream process. Three kinds of room, oven, freeze and supercritical drying methods were used in this step. Drying can change BC's characteristic; therefore, it should be chosen very carefully [92].

8. FORMS OF BACTERIAL CELLULOSE

Intact membrane, disassembled BC and BC nanocrystals are three BC forms [41, 93, 94]. An intact membrane can be immersed in dispersion with other materials. This has the advantage of simpler disintegration from other materials but cannot change the fermentation process [50, 93, 94]. BC membrane on the other hand, can be disassembled, and therefore they are easier to integrate with other materials and even become better powder and film [95 - 97]. BC nanocrystal

has been produced by acid hydrolysis, which removes the amorphous of the cellulose [98].

9. STRUCTURE OF BACTERIAL CELLULOSE

Cellulose indeed is polysaccharide consisting of carbon, hydrogen, and oxygen. This carbohydrate polymeric structure composes of glucose units. The role of cellulose in the bacterial film is stability towards different chemical or temperature environments. High mechanical strength, crystallinity, and ultra-fine and pure fiber network are very dependent on highly insoluble and inelastic cellulose fibrils. Pore and tunnels within the thin layer (pellicle) of bacterial cellulose can retain water 16 times higher than plant cellulose [99].

The cellulose pellicle was formed on the upper surface of air/ media, which shows the importance of oxygen for this process. The pellicle of bacterial cellulose with 15 GPa (Young modulus) [100] is considered as a very tough polymeric film. This unique structure is related to fibrils conformation, which is bound tightly by hydrogen bonds. The supermolecular structures of aligned glucan chains with inter and intrachain hydrogen bonds formed the microfibrils (Fig. 7). These microfibrils randomly assemble the fibrils, which literally construct the bacterial cellulose pellicle. It is noteworthy that bacterial cellulose belongs crystallographically to Cellulose I, which means the crystalline fibrils are in parallel arrangement [101]. Various types of irregularities of fibrils structures of cellulose (kinks or twists of the microfibrils and capillaries) provide the structural heterogeneity with much greater surface area compared to smooth fiber (Fig. 7).

10. MAIN APPLICATIONS OF BC

BC is recognized by the US food and drug administration as generally safe (GRAS) food [16]. As a fiber, BC is considered good indigestible food and prescribed in humans as dietetic food [102, 103]. One of the most famous BC is Nata-de-coco, which is the BC grown from coconut water with carbohydrates and amino acid. This cubic BC is immersed in sugar syrup [104].




Fig. (7). Structure of Bacterial cellulose.

The product export reached 6.6 billion USD in 2011 [105]. This kind of BC can be considered low calorie desserts / snacks and plays a great role as a novel foamy and crunchy product. On the other hand, the fats in the food are always associated with several health problems such as obesity, diabetes, high blood cholesterol levels, and heart diseases, therefore, replacing the fat with BC can help to improve the food industry and human health [106 - 108]. BC is already used in meatballs upto 20% or 10% [42, 55].

Meat is analogous with BC and the mold *Monascus purpureus* was prepared and introduced with many advantages such as antihypercholesterole. This *Monascus*-BC complex can be a good substitute for consumers with special dietary restrictions [58, 109, 110]. Furthermore, BC was used as a thicker food product to increase the strength in gelling products and water binding. Also, it was applied as a stabilizer of Pickering emulsions [13, 111]. As an immobilizing agent of probiotics and enzyme, BC also has great attention for many researchers [112, 113]. It is noteworthy to mention that lipase, laccase and lysozyme immobilized by BC were reported by researchers [114 - 116].

BC applications in food packaging as a film and coating were also reported by many researchers [117]. Impregnating BC with other polymers could bring many advantages to the composites. BC-chitosan produced by researchers recently showed the antimicrobial activity against gram-positive and gram-negative bacteria beside the better elastic property [118].

In the biomedical application of BC, several BC-composites were developed by researchers. The wound healing, skin and tissue regeneration, healing under infectious environment, development of artificial organs, blood vessels, skin substitutes, and many devices such as conducting devices, displays, optoelectronics, sensors and biosensors have been reported recently [18, 102, 119, 120].

CONCLUSION

Many challenges need to be addressed in BC research, such as introducing low-cost medium and efficient producing system with low capital investment. Besides many applications of BC and BC-composites, the need to study bacterial diversity is necessary. Furthermore, the study of 3-D printing of BC for food and food packages with specific geometry can provide more information in this field. Additionally, BC producers' diversity and molecular characterization can give great insight on low cost production of BC, especially for food and biomedical products. Last but not least, engineering the BC producers towards specific functionalization can answer many industrial and biomedical needs. Tunable control on BC production and novel structural pattern can be important for BC producer bacteria's future engineering.

CONSENT FOR PUBLICATION

Not applicable.

FUNDING

This work was financially supported by the Institute For Research and Development, Suan Sunandha Rajabhat

University (SSRU) (Grant number 441/2563).

CONFLICT OF INTEREST

The authors declare no conflict of interest, financial or otherwise.

ACKNOWLEDGEMENTS

The authors would like to thank Dr. Anat Thapinta, Dean of the Faculty of Science and Technology, SSRU and Dr. Suwaree Yordchim, Director of the Institute of Research and Development, SSRU for their outstanding support. Wirongrong Thamyo is acknowledged for excellent secretarial assistance.

REFERENCES

- [1] Rajwade JM, Paknikar KM, Kumbhar JV. Applications of bacterial cellulose and its composites in biomedicine. *Appl Microbiol Biotechnol* 2015; 99(6): 2491-511. [http://dx.doi.org/10.1007/s00253-015-6426-3] [PMID: 25666681]
- [2] Ruka DR, Simon GP, Dean KM. Altering the growth conditions of *Gluconacetobacter xylinus* to maximize the yield of bacterial cellulose. *Carbohydr Polym* 2012; 89(2): 613-22. [http://dx.doi.org/10.1016/j.carbpol.2012.03.059] [PMID: 24750766]
- [3] Chen S-Q, Lopez-Sanchez P, Wang D, Mikkelsen D, Gidley MJ. Mechanical properties of bacterial cellulose synthesised by diverse strains of the genus *Komagataeibacter*. *Food Hydrocoll* 2018; 81: 87-95. [http://dx.doi.org/10.1016/j.foodhyd.2018.02.031]
- [4] Marsh AJ, O'Sullivan O, Hill C, Ross RP, Cotter PD. Sequence-based analysis of the bacterial and fungal compositions of multiple kombucha (tea fungus) samples. *Food Microbiol* 2014; 38: 171-8. [http://dx.doi.org/10.1016/j.fm.2013.09.003] [PMID: 24290641]
- [5] Reiniati I, Hrymak AN, Margaritis A. Recent developments in the production and applications of bacterial cellulose fibers and nanocrystals. *Crit Rev Biotechnol* 2017; 37(4): 510-24. [http://dx.doi.org/10.1080/07388551.2016.1189871] [PMID: 27248159]
- [6] Chawla P, Bajaj I, Survase S, Singhal R. Microbial cellulose: fermentative production and applications. *Food Technol Biotechnol* 2009; 47: 107-24.
- [7] Lee KY, Buldum G, Mantalaris A, Bismarck A. More than meets the eye in bacterial cellulose: biosynthesis, bioprocessing, and applications in advanced fiber composites. *Macromol Biosci* 2014; 14(1): 10-32. [http://dx.doi.org/10.1002/mabi.201300298] [PMID: 23897676]
- [8] Huang Y, Zhu C, Yang J, Nie Y, Chen C, Sun D. Recent advances in bacterial cellulose. *Cellulose* 2014; 21(1): 1-30. [http://dx.doi.org/10.1007/s10570-013-0088-z]
- [9] Samfira I, Butnariu M, Rodino S, Butu M. Structural investigation of mistletoe plants from various hosts exhibiting diverse lignin phenotypes. *Dig J Nanomater Biostruct* 2013; 8: 1679-86.
- [10] Siró I, Plackett D. Microfibrillated cellulose and new nanocomposite materials: a review. *Cellulose* 2010; 17(3): 459-94. [http://dx.doi.org/10.1007/s10570-010-9405-y]
- [11] Iguchi M. Review bacterial cellulose a masterpiece of natures arts. *J Mater Sci* 2000; 35: 1-10. [http://dx.doi.org/10.1023/A:1004775229149]
- [12] Tsouko E, Kourmentza C, Ladakis D, et al. Bacterial cellulose production from industrial waste and by-product streams. *Int J Mol Sci* 2015; 16(7): 14832-49. [http://dx.doi.org/10.3390/ijms160714832] [PMID: 26140376]
- [13] Paximada P, Tsouko E, Kopsahelis N, Koutinas AA, Mandala I. Bacterial cellulose as stabilizer of o/w emulsions. *Food Hydrocoll* 2016; 53: 225-32. [http://dx.doi.org/10.1016/j.foodhyd.2014.12.003]
- [14] Sulaeva I, Henniges U, Rosenau T, Potthast A. Bacterial cellulose as a material for wound treatment: Properties and modifications. A review. *Biotechnol Adv* 2015; 33(8): 1547-71. [http://dx.doi.org/10.1016/j.biotechadv.2015.07.009] [PMID: 26253857]
- [15] Meftahi A, Khajavi R, Rashidi A, Sattari M, Yazdanshenas M, Torabi M. The effects of cotton gauze coating with microbial cellulose. *Cellulose* 2010; 17(1): 199-204. [http://dx.doi.org/10.1007/s10570-009-9377-y]

- [16] Shi Z, Zhang Y, Phillips GO, Yang G. Utilization of bacterial cellulose in food. *Food Hydrocoll* 2014; 35: 539-45. [http://dx.doi.org/10.1016/j.foodhyd.2013.07.012]
- [17] Gelin K, Bodin A, Gatenholm P, Mhrranyan A, Edwards K, Strømme M. Characterization of water in bacterial cellulose using dielectric spectroscopy and electron microscopy. *Polymer (Guildf)* 2007; 48(26): 7623-31. [http://dx.doi.org/10.1016/j.polymer.2007.10.039]
- [18] Shah N, Ul-Islam M, Khattak WA, Park JK. Overview of bacterial cellulose composites: a multipurpose advanced material. *Carbohydr Polym* 2013; 98(2): 1585-98. [http://dx.doi.org/10.1016/j.carbpol.2013.08.018] [PMID: 24053844]
- [19] Jozala AF, Pértile RAN, dos Santos CA, et al. Bacterial cellulose production by *Gluconacetobacter xylinus* by employing alternative culture media. *Appl Microbiol Biotechnol* 2015; 99(3): 1181-90. [http://dx.doi.org/10.1007/s00253-014-6232-3] [PMID: 25472434]
- [20] Fan X, Gao Y, He W, et al. Production of nano bacterial cellulose from beverage industrial waste of citrus peel and pomace using *Komagataeibacter xylinus*. *Carbohydr Polym* 2016; 151: 1068-72. [http://dx.doi.org/10.1016/j.carbpol.2016.06.062] [PMID: 27474656]
- [21] Molina-Ramirez C, Castro C, Zuluaga R, Gañán P. Physical characterization of bacterial cellulose produced by *komagataeibacter medellinensis* using food supply chain waste and agricultural by-products as alternative low-cost feedstocks. *J Polym Environ* 2018; 26(2): 830-7. [http://dx.doi.org/10.1007/s10924-017-0993-6]
- [22] Revin V, Liyaskina E, Nazarkina M, Bogatyreva A, Shchankin M. Cost-effective production of bacterial cellulose using acidic food industry by-products. *Braz J Microbiol* 2018; 49(Suppl. 1): 151-9. [http://dx.doi.org/10.1016/j.bjm.2017.12.012] [PMID: 29703527]
- [23] Pacheco G, Nogueira CR, Meneguim AB, Trovatti E, Silva MC, Machado RT, et al. Development and characterization of bacterial cellulose produced by cashew tree residues as alternative carbon source. *Ind Crops Prod* 2017; 107: 13-9. [http://dx.doi.org/10.1016/j.indcrop.2017.05.026]
- [24] Lin S-P, Calvar IL, Catchmark JM, Liu J-R, Demirci A, Cheng K-C. Biosynthesis, production and applications of bacterial cellulose. *Cellulose* 2013; 20(5): 2191-219. [http://dx.doi.org/10.1007/s10570-013-9994-3]
- [25] Rangaswamy B. K P V, Hungund B. Microbial cellulose production from bacteria isolated from rotten fruit. *Int J Polym Sci* 2015; 2015: 1-8. [http://dx.doi.org/10.1155/2015/280784]
- [26] Hareesh E. abdul faisal P, Benjamin S. Optimization of parameters for the production of cellulase from *Achromobacter xylosoxidans* BSS4 by solid-state fermentation. *Electro J Bio* 2016; 4: 443-8.
- [27] Gorgieva S, Trček J. Bacterial Cellulose: Production, modification and perspectives in biomedical applications. *Nanomaterials (Basel)* 2019; 9(10)E1352 [http://dx.doi.org/10.3390/nano9101352] [PMID: 31547134]
- [28] Sunagawa N, Tajima K, Hosoda M, et al. Cellulose production by *Enterobacter* sp. CJF-002 and identification of genes for cellulose biosynthesis. *Cellulose* 2012; 19(6): 1989-2001. [http://dx.doi.org/10.1007/s10570-012-9777-2]
- [29] Zhao H, Xia J, Wang J, et al. Production of bacterial cellulose using polysaccharide fermentation wastewater as inexpensive nutrient sources. *Biotechnol Biotechnol Equip* 2018; 32(2): 350-6. [http://dx.doi.org/10.1080/13102818.2017.1418673]
- [30] Matthyse AG, Thomas DL, White AR. Mechanism of cellulose synthesis in *Agrobacterium tumefaciens*. *J Bacteriol* 1995; 177(4): 1076-81. [http://dx.doi.org/10.1128/JB.177.4.1076-1081.1995] [PMID: 7860586]
- [31] Matthyse AG. Role of bacterial cellulose fibrils in *Agrobacterium tumefaciens* infection. *J Bacteriol* 1983; 154(2): 906-15. [http://dx.doi.org/10.1128/JB.154.2.906-915.1983] [PMID: 6302086]
- [32] Matthyse AG, White S, Lightfoot R. Genes required for cellulose synthesis in *Agrobacterium tumefaciens*. *J Bacteriol* 1995; 177(4): 1069-75. [http://dx.doi.org/10.1128/JB.177.4.1069-1075.1995] [PMID: 7860585]
- [33] Matthyse AG. Attachment of *Agrobacterium* to plant surfaces. *Front Plant Sci* 2014; 5: 252. [http://dx.doi.org/10.3389/fpls.2014.00252] [PMID: 24926300]
- [34] Costa AFS, Almeida FCG, Vinhas GM, Sarubbo LA. Production of bacterial cellulose by *Gluconacetobacter hansenii* using corn steep liquor as nutrient sources. *Front Microbiol* 2017; 8: 2027. [http://dx.doi.org/10.3389/fmicb.2017.02027] [PMID: 29089941]
- [35] Du R, Zhao F, Peng Q, Zhou Z, Han Y. Production and characterization of bacterial cellulose produced by *Gluconacetobacter xylinus* isolated from Chinese persimmon vinegar. *Carbohydr Polym* 2018; 194: 200-7. [http://dx.doi.org/10.1016/j.carbpol.2018.04.041] [PMID: 29801830]
- [36] Raheem Kazim A. Production, optimization, and characterization of cellulose produced from *Pseudomonas* spp. *World Journal of Experimental Biosciences* 2015; 3(2): 89-93.
- [37] Ahmed S, Raheem Kazim A, Mahmood H. Increasing Cellulose Production from *Rhizobium leguminosarum* bv. viciae. *Journal of Al-Nahrain University- Science* 2017; 20(1): 120-5.
- [38] Robledo M, Rivera L, Jiménez-Zurdo JI, et al. Role of *Rhizobium* endoglucanase CelC2 in cellulose biosynthesis and biofilm formation on plant roots and abiotic surfaces. *Microb Cell Fact* 2012; 11: 125. [http://dx.doi.org/10.1186/1475-2859-11-125] [PMID: 22970813]
- [39] Moniri M, Boroumand Moghaddam A, Azizi S, et al. Production and status of bacterial cellulose in biomedical engineering. *Nanomaterials (Basel)* 2017; 7(9): 257. [http://dx.doi.org/10.3390/nano7090257] [PMID: 32962322]
- [40] Ji K, Wang W, Zeng B, et al. Bacterial cellulose synthesis mechanism of facultative anaerobe *Enterobacter* sp. FY-07. *Sci Rep* 2016; 6: 21863. [http://dx.doi.org/10.1038/srep21863] [PMID: 26911736]
- [41] Ul-Islam M, Khan S, Ullah MW, Park JK. Bacterial cellulose composites: Synthetic strategies and multiple applications in biomedical and electro-conductive fields. *Biotechnol J* 2015; 10(12): 1847-61. [http://dx.doi.org/10.1002/biot.201500106] [PMID: 26395011]
- [42] Liu M, Li S, Xie Y, et al. Enhanced bacterial cellulose production by *Gluconacetobacter xylinus* via expression of *Vitreoscilla* hemoglobin and oxygen tension regulation. *Appl Microbiol Biotechnol* 2018; 102(3): 1155-65. [http://dx.doi.org/10.1007/s00253-017-8680-z] [PMID: 29199354]
- [43] Florea M, Hagemann H, Santosa G, et al. Engineering control of bacterial cellulose production using a genetic toolkit and a new cellulose-producing strain. *Proc Natl Acad Sci USA* 2016; 113(24): E3431-40. [http://dx.doi.org/10.1073/pnas.1522985113] [PMID: 27247386]
- [44] Hungund B, Prabhu S, Shetty C, Acharya S, Prabhu V, Gupta S. Production of bacterial cellulose from *Gluconacetobacter persimmonis* GH-2 using dual and cheaper carbon sources. *J Microb Biochem Technol* 2013; 5(2): 31-3. [http://dx.doi.org/10.4172/1948-5948.1000095]
- [45] Cacicedo ML, Castro MC, Servetas I, et al. Progress in bacterial cellulose matrices for biotechnological applications. *Bioresour Technol* 2016; 213: 172-80. [http://dx.doi.org/10.1016/j.biortech.2016.02.071] [PMID: 26927233]
- [46] Kurosuni A, Sasaki C, Yamashita Y, Nakamura Y. Utilization of various fruit juices as carbon source for production of bacterial cellulose by *Acetobacter xylinum* NBRC 13693. *Carbohydr Polym* 2009; 76(2): 333-5. [http://dx.doi.org/10.1016/j.carbpol.2008.11.009]
- [47] Keshk S, Sameshima K. The utilization of sugar cane molasses with/without the presence of lignosulfonate for the production of bacterial cellulose. *Appl Microbiol Biotechnol* 2006; 72(2): 291-6. [http://dx.doi.org/10.1007/s00253-005-0265-6] [PMID: 16450110]
- [48] Tyagi N, Suresh S. Production of cellulose from sugarcane molasses using *Gluconacetobacter intermedius* SNT-1: optimization & characterization. *J Clean Prod* 2016; 112: 71-80. [http://dx.doi.org/10.1016/j.jclepro.2015.07.054]
- [49] Shezad O, Khan S, Khan T, Park JK. Production of bacterial cellulose in static conditions by a simple fed-batch cultivation strategy. *Korean J Chem Eng* 2009; 26(6): 1689-92. [http://dx.doi.org/10.1007/s11814-009-0232-5]
- [50] Ul-Islam M, Khan T, Park JK. Water holding and release properties of bacterial cellulose obtained by in situ and ex situ modification. *Carbohydr Polym* 2012; 88(2): 596-603. a [http://dx.doi.org/10.1016/j.carbpol.2012.01.006]
- [51] Ul-Islam M, Khan T, Park JK. Nanoreinforced bacterial cellulose-montmorillonite composites for biomedical applications. *Carbohydr Polym* 2012; 89(4): 1189-97. b [http://dx.doi.org/10.1016/j.carbpol.2012.03.093] [PMID: 24750931]
- [52] Ahmed S, Kanchi S, Kumar G. Handbook of biopolymers: Advances and multifaceted applications. New York: Jenny Stanford Publishing 2018. [http://dx.doi.org/10.1201/9780429024757]

- [53] Zahan KA. 'Pa'e N, Muhamad II. Monitoring the effect of pH on bacterial cellulose production and *Acetobacter xylinum* 0416 Growth in a Rotary Discs Reactor. Arab J Sci Eng 2015; 40(7): 1881-5. [http://dx.doi.org/10.1007/s13369-015-1712-z]
- [54] Wu SC, Li MH. Production of bacterial cellulose membranes in a modified airlift bioreactor by *Gluconacetobacter xylinus*. J Biosci Bioeng 2015; 120(4): 444-9. [http://dx.doi.org/10.1016/j.jbiosc.2015.02.018] [PMID: 25823854]
- [55] Lin D, Lopez-Sanchez P, Li R, Li Z. Production of bacterial cellulose by *Gluconacetobacter hansenii* CGMCC 3917 using only waste beer yeast as nutrient source. Bioresour Technol 2014; 151: 113-9. [http://dx.doi.org/10.1016/j.biortech.2013.10.052] [PMID: 24212131]
- [56] Esa F, Tasirin SM, Rahman NA. Overview of bacterial cellulose production and application. Agric Agric Sci Procedia 2014; 2: 113-9. [http://dx.doi.org/10.1016/j.aaspro.2014.11.017]
- [57] Kralisch D, Hessler N, Klemm D, Erdmann R, Schmidt W. White biotechnology for cellulose manufacturing--the HoLiR concept. Biotechnol Bioeng 2010; 105(4): 740-7. [PMID: 19816981]
- [58] Kim D, Ku S. Beneficial effects of *Monascus* sp. KCCM 10093 pigments and derivatives: a mini review. Molecules 2018; 23(1): 98. [http://dx.doi.org/10.3390/molecules23010098] [PMID: 29301350]
- [59] Hornung M, Ludwig M, Schmauder H. Optimizing the production of bacterial cellulose in surface culture: a novel aerosol bioreactor working on a fed batch principle (Part 3). Eng Life Sci 2007; 7(1): 35-41. [http://dx.doi.org/10.1002/elsc.200620164]
- [60] Park JK, Hyun SH, Jung JY. Conversion of *G. hansenii* PJK into non-cellulose-producing mutants according to the culture condition. Biotechnol Bioprocess Eng; BBE 2004; 9(5): 383. [http://dx.doi.org/10.1007/BF02933062]
- [61] Son HJ, Heo MS, Kim YG, Lee SJ. Optimization of fermentation conditions for the production of bacterial cellulose by a newly isolated *Acetobacter* sp. A9 in shaking cultures. Biotechnol Appl Biochem 2001; 33(1): 1-5. [http://dx.doi.org/10.1042/BA20000065] [PMID: 11171030]
- [62] Shoda M, Sugano Y. Recent advances in bacterial cellulose production. Biotechnol Bioprocess Eng; BBE 2005; 10(1): 1. [http://dx.doi.org/10.1007/BF02931175]
- [63] Watanabe K, Tabuchi M, Morinaga Y, Yoshinaga F. Structural features and properties of bacterial cellulose produced in agitated culture. Cellulose 1998; 5(3): 187-200. [http://dx.doi.org/10.1023/A:1009272904582]
- [64] Chao Y-p, Sugano Y, Kouda T, Yoshinaga F, Shoda M. Production of bacterial cellulose by *Acetobacter xylinum* with an airlift reactor. Biotechnol Tech 1997; 11(11): 829-32. [http://dx.doi.org/10.1023/A:1018433526709]
- [65] Heukelekian H, Heller A. Relation between food concentration and surface for bacterial growth. J Bacteriol 1940; 40(4): 547-58. [http://dx.doi.org/10.1128/JB.40.4.547-558.1940] [PMID: 16560368]
- [66] Zobell CE. The Effect of solid surfaces upon bacterial activity. J Bacteriol 1943; 46(1): 39-56. [http://dx.doi.org/10.1128/JB.46.1.39-56.1943] [PMID: 16560677]
- [67] Jones HC, Roth IL, Sanders WM III. Electron microscopic study of a slime layer. J Bacteriol 1969; 99(1): 316-25. [http://dx.doi.org/10.1128/JB.99.1.316-325.1969] [PMID: 5802613]
- [68] Characklis WG. Attached microbial growths--II. Frictional resistance due to microbial slimes. Water Res 1973; 7(9): 1249-58. [http://dx.doi.org/10.1016/0043-1354(73)90002-X]
- [69] Costerton JW, Geesey GG, Cheng KJ. How bacteria stick. Sci Am 1978; 238(1): 86-95. [http://dx.doi.org/10.1038/scientificamerican0178-86] [PMID: 635520]
- [70] Fletcher M, Loeb GI. Influence of substratum characteristics on the attachment of a marine pseudomonad to solid surfaces. Appl Environ Microbiol 1979; 37(1): 67-72. [http://dx.doi.org/10.1128/AEM.37.1.67-72.1979] [PMID: 16345338]
- [71] Pringle JH, Fletcher M. Influence of substratum wettability on attachment of freshwater bacteria to solid surfaces. Appl Environ Microbiol 1983; 45(3): 811-7. [http://dx.doi.org/10.1128/AEM.45.3.811-817.1983] [PMID: 16346243]
- [72] Bendinger B, Rijnaarts HH, Altendorf K, Zehnder AJ. Physicochemical cell surface and adhesive properties of coryneform bacteria related to the presence and chain length of mycolic acids. Appl Environ Microbiol 1993; 59(11): 3973-7. [http://dx.doi.org/10.1128/AEM.59.11.3973-3977.1993] [PMID: 16349100]
- [73] Dawson LF, Valiente E, Faulds-Pain A, Donahue EH, Wren BW. Characterisation of *Clostridium difficile* biofilm formation, a role for Spo0A. PLoS One 2012; 7(12): e50527 [http://dx.doi.org/10.1371/journal.pone.0050527] [PMID: 23236376]
- [74] Bales PM, Renke EM, May SL, Shen Y, Nelson DC. Purification and characterization of biofilm-associated EPS Exopolysaccharides from ESKAPE organisms and other pathogens. PLoS One 2013; 8(6): e67950 [http://dx.doi.org/10.1371/journal.pone.0067950] [PMID: 23805330]
- [75] Loeb GI, Neihof RA. Marine conditioning films Applied Chemistry at Protein Interfaces Advances in Chemistry 145. American Chemical Society 1975; pp. 319-35. [http://dx.doi.org/10.1021/ba-1975-0145.ch016]
- [76] Colvin KM, Irie Y, Tart CS, et al. The Pel and Psl polysaccharides provide *Pseudomonas aeruginosa* structural redundancy within the biofilm matrix. Environ Microbiol 2012; 14(8): 1913-28. [http://dx.doi.org/10.1111/j.1462-2920.2011.02657.x] [PMID: 22176658]
- [77] Rijnaarts HH, Norde W, Bouwer EJ, Lyklema J, Zehnder AJ. Bacterial adhesion under static and dynamic conditions. Appl Environ Microbiol 1993; 59(10): 3255-65. [http://dx.doi.org/10.1128/AEM.59.10.3255-3265.1993] [PMID: 16349063]
- [78] Zheng D, Taylor GT, Gyananath G. Influence of laminar flow velocity and nutrient concentration on attachment of marine bacterioplankton. Biofouling 1994; 8(2): 107-20. [http://dx.doi.org/10.1080/08927019409378266]
- [79] Mika F, Hengge R. Small RNAs in the control of RpoS, CsgD, and biofilm architecture of *Escherichia coli*. RNA Biol 2014; 11(5): 494-507. [http://dx.doi.org/10.4161/rna.28867] [PMID: 25028968]
- [80] Donlan RM, Pipes WO, Yohe TL. Biofilm formation on cast iron substrata in water distribution systems. Water Res 1994; 28(6): 1497-503. [http://dx.doi.org/10.1016/0043-1354(94)90318-2]
- [81] Fera P, Siebel MA, Characklis WG, Prieur D. Seasonal variations in bacterial colonisation of stainless steel, aluminium and polycarbonate surfaces in a sea water flow system. Biofouling 1989; 1(3): 251-61. [http://dx.doi.org/10.1080/08927018909378112]
- [82] Fletcher M. Attachment of *Pseudomonas fluorescens* to glass and influence of electrolytes on bacterium-substratum separation distance. J Bacteriol 1988; 170(5): 2027-30. [http://dx.doi.org/10.1128/JB.170.5.2027-2030.1988] [PMID: 3129399]
- [83] Kurzbaum E, Iliasafav L, Kolik L, et al. From the Titanic and other shipwrecks to biofilm prevention: The interesting role of polyphenol-protein complexes in biofilm inhibition. Sci Total Environ 2019; 658: 1098-105. [http://dx.doi.org/10.1016/j.scitotenv.2018.12.197] [PMID: 30677974]
- [84] Bartowsky EJ, Henschke PA. Acetic acid bacteria spoilage of bottled red wine -- a review. Int J Food Microbiol 2008; 125(1): 60-70. [http://dx.doi.org/10.1016/j.ijfoodmicro.2007.10.016] [PMID: 18237809]
- [85] Rosenberg M, Kjelleberg S. Hydrophobic Interactions: Role in Bacterial Adhesion. Advances in Microbial Ecology Boston, MA. Springer, US 1986; pp. 353-93. [http://dx.doi.org/10.1007/978-1-4757-0611-6_8]
- [86] Rosenberg M, Bayer EA, Delarea J, Rosenberg E. Role of thin fimbriae in adherence and growth of *Acinetobacter calcoaceticus* RAG-1 on hexadecane. Appl Environ Microbiol 1982; 44(4): 929-37. [http://dx.doi.org/10.1128/AEM.44.4.929-937.1982] [PMID: 16346118]
- [87] Bullitt E, Makowski L. Structural polymorphism of bacterial adhesion pili. Nature 1995; 373(6510): 164-7. [http://dx.doi.org/10.1038/373164a0] [PMID: 7816100]
- [88] Bashan Y, Levanyon H. Active attachment of *Azospirillum brasilense* Cd to Quartz Sand and to a Light-textured Soil by Protein Bridging. Microbiology 1988; 134(8): 2269-79. [http://dx.doi.org/10.1099/00221287-134-8-2269]
- [89] Davies DG, Geesey GG. Regulation of the alginate biosynthesis gene *algC* in *Pseudomonas aeruginosa* during biofilm development in continuous culture. Appl Environ Microbiol 1995; 61(3): 860-7. [http://dx.doi.org/10.1128/AEM.61.3.860-867.1995] [PMID: 7793920]
- [90] Prigent-Combaret C, Vidal O, Dorel C, Lejeune P. Abiotic surface sensing and biofilm-dependent regulation of gene expression in *Escherichia coli*. J Bacteriol 1999; 181(19): 5993-6002. [http://dx.doi.org/10.1128/JB.181.19.5993-6002.1999] [PMID: 10552002]

- 10498711]
- [91] Becker P, Hufnagle W, Peters G, Herrmann M. Detection of differential gene expression in biofilm-forming versus planktonic populations of *Staphylococcus aureus* using micro-representational-difference analysis. *Appl Environ Microbiol* 2001; 67(7): 2958-65. [http://dx.doi.org/10.1128/AEM.67.7.2958-2965.2001] [PMID: 11425708]
- [92] Zeng M, Laromaine A, Roig A. Bacterial cellulose films: influence of bacterial strain and drying route on film properties. *Cellulose* 2014; 21(6): 4455-69. [http://dx.doi.org/10.1007/s10570-014-0408-y]
- [93] Zhu H, Jia S, Yang H, Tang W, Jia Y, Tan Z. Characterization of bacteriostatic sausage casing: a composite of bacterial cellulose embedded with ϵ -polylysine. *Food Sci Biotechnol* 2010; 19(6): 1479-84. [http://dx.doi.org/10.1007/s10068-010-0211-y]
- [94] Chang S-T, Chen L-C, Lin S-B, Chen H-H. Nano-biomaterials application: Morphology and physical properties of bacterial cellulose/gelatin composites via crosslinking. *Food Hydrocoll* 2012; 27(1): 137-44. [http://dx.doi.org/10.1016/j.foodhyd.2011.08.004]
- [95] Guo Y, Zhang X, Hao W, *et al.* Nano-bacterial cellulose/soy protein isolate complex gel as fat substitutes in ice cream model. *Carbohydr Polym* 2018; 198: 620-30. [http://dx.doi.org/10.1016/j.carbpol.2018.06.078] [PMID: 30093042]
- [96] Jiang C, Oporto GS, Zhong T, Jaczynski J. TEMPO nanofibrillated cellulose as template for controlled release of antimicrobial copper from PVA films. *Cellulose* 2016; 23(1): 713-22. [http://dx.doi.org/10.1007/s10570-015-0834-5]
- [97] Viana RM, Sá NMSM, Barros MO, Borges MF, Azeredo HMC. Nanofibrillated bacterial cellulose and pectin edible films added with fruit purees. *Carbohydr Polym* 2018; 196: 27-32. [http://dx.doi.org/10.1016/j.carbpol.2018.05.017] [PMID: 29891296]
- [98] O'Connor B, Berry R, Goguen R. Commercialization of cellulose nanocrystal (NCC™) production: A business case focusing on the importance of proactive EHS management. *Nanotechnology environmental health and safety*. Elsevier 2014; pp. 225-46.
- [99] dos Santos MA, Grenha A. Polysaccharide nanoparticles for protein and Peptide delivery: exploring less-known materials. *Adv Protein Chem Struct Biol* 2015; 98: 223-61. [http://dx.doi.org/10.1016/bs.apcsb.2014.11.003] [PMID: 25819281]
- [100] Vigentini I, Fabrizio V, Dellacà F, Rossi S, Azario I, Mondin C, *et al.* Set-up of bacterial cellulose production from the genus *Komagataeibacter* and its use in a gluten-free bakery product as a case study. *Front Microbiol* 2019; 10: 31551945 [PMID: 31551945]
- [101] Jacek P, Dourado F, Gama M, Bielecki S. Molecular aspects of bacterial nanocellulose biosynthesis. *Microb Biotechnol* 2019; 12(4): 633-49. [http://dx.doi.org/10.1111/1751-7915.13386] [PMID: 30883026]
- [102] Mohite BV, Patil SV. A novel biomaterial: bacterial cellulose and its new era applications. *Biotechnol Appl Biochem* 2014; 61(2): 101-10. [http://dx.doi.org/10.1002/bab.1148] [PMID: 24033726]
- [103] Fontana JD, Koop HS, Tiboni M, Grzybowski A, Pereira A, Kruger CD, *et al.* New insights on bacterial cellulose Food biosynthesis. Elsevier 2017; pp. 213-49.
- [104] Zhang J, Yang Y, Deng J, Wang Y, Hu Q, Li C, *et al.* Dynamic profile of the microbiota during coconut water pre-fermentation for nata de coco production. *Lebensm Wiss Technol* 2017; 81: 87-93. [http://dx.doi.org/10.1016/j.lwt.2017.03.036]
- [105] Piadozo MES. Nata de coco industry in the Philippines Bacterial nanocellulose. Elsevier 2016; pp. 215-29. [http://dx.doi.org/10.1016/B978-0-444-63458-0.00013-5]
- [106] Rios RV, Garzón R, Lannes SCS, Rosell CM. Use of succinyl chitosan as fat replacer on cake formulations. *LWT* 2018; 96: 260-5. [http://dx.doi.org/10.1016/j.lwt.2018.05.041]
- [107] Kumar Y, Kairam N, Ahmad T, Yadav DN. Physico chemical, microstructural and sensory characteristics of low fat meat emulsion containing aloe gel as potential fat replacer. *Int J Food Sci Technol* 2016; 51(2): 309-16. [http://dx.doi.org/10.1111/ijfs.12957]
- [108] Aydinol P, Ozcan T. Production of reduced fat Labneh cheese with inulin and β -glucan fibre based fat replacer. *Int J Dairy Technol* 2018; 71(2): 362-71. [http://dx.doi.org/10.1111/1471-0307.12456]
- [109] Sheu F, Wang CL, Shyu YT. Fermentation of *Monascus purpureus* on bacterial cellulose-nata and the color stability of monascus-nata complex. *J Food Sci* 2000; 65(2): 342-5. [http://dx.doi.org/10.1111/j.1365-2621.2000.tb16004.x]
- [110] Ullah H, Santos HA, Khan T. Applications of bacterial cellulose in food, cosmetics and drug delivery. *Cellulose* 2016; 23(4): 2291-314. [http://dx.doi.org/10.1007/s10570-016-0986-y]
- [111] Dankovich TA, Gray DG. Contact angle measurements on smooth nanocrystalline cellulose (I) thin films. *J Adhes Sci Technol* 2011; 25(6-7): 699-708. [http://dx.doi.org/10.1163/016942410X525885]
- [112] Chávarri M, Marañón I, Villarán MC. Encapsulation technology to protect probiotic bacteria. *Probiotics*. IntechOpen 2012. [http://dx.doi.org/10.5772/50046]
- [113] Fijałkowski K, Peitler D, Rakoczy R, Żywicka A. Survival of probiotic lactic acid bacteria immobilized in different forms of bacterial cellulose in simulated gastric juices and bile salt solution. *Lebensm Wiss Technol* 2016; 68: 322-8. [http://dx.doi.org/10.1016/j.lwt.2015.12.038]
- [114] Wu S-C, Wu S-M, Su F-M. Novel process for immobilizing an enzyme on a bacterial cellulose membrane through repeated absorption. *J Chem Technol Biotechnol* 2017; 92(1): 109-14. [http://dx.doi.org/10.1002/jctb.4994]
- [115] Chen P, Cho SY, Jin H-J. Modification and applications of bacterial celluloses in polymer science. *Macromol Res* 2010; 18(4): 309-20. [http://dx.doi.org/10.1007/s13233-010-0404-5]
- [116] Bayazidi P, Almasi H, Asl AK. Immobilization of lysozyme on bacterial cellulose nanofibers: Characteristics, antimicrobial activity and morphological properties. *Int J Biol Macromol* 2018; 107(Pt B): 2544-51. [http://dx.doi.org/10.1016/j.ijbiomac.2017.10.137] [PMID: 29079438]
- [117] Otoni CG, Avena-Bustillos RJ, Azeredo HM, Lorevice MV, Moura MR, Mattoso LH, *et al.* Recent advances on edible films based on fruits and vegetables—a review. *Compr Rev Food Sci Food Saf* 2017; 16(5): 1151-69. [http://dx.doi.org/10.1111/1541-4337.12281]
- [118] Ross P, Mayer R, Benziman M. Cellulose biosynthesis and function in bacteria. *Microbiol Rev* 1991; 55(1): 35-58. [http://dx.doi.org/10.1128/MMBR.55.1.35-58.1991] [PMID: 2030672]
- [119] Meng N, Zhou N-L, Zhang S-Q, Shen J. Synthesis and antimicrobial activities of polymer/montmorillonite-chlorhexidine acetate nanocomposite films. *Appl Clay Sci* 2009; 42(3): 667-70. [http://dx.doi.org/10.1016/j.clay.2008.06.016]
- [120] Czaja WK, Young DJ, Kawecki M, Brown RM Jr. The future prospects of microbial cellulose in biomedical applications. *Biomacromolecules* 2007; 8(1): 1-12. [http://dx.doi.org/10.1021/bm060620d] [PMID: 17206781]